

## PRIMER FOR DURACON<sup>®</sup> FLOORING SYSTEMS

### KEY BENEFIT SUMMARY

- Excellent adhesion to most common substrates
- Fast and safe curing even at low temperatures
- Provides good adhesion to subsequent coats

## PRODUCT INFORMATION

### Description

Duracon<sup>®</sup> 101 is a low viscosity, colourless, 2 component reactive resin based on methyl methacrylate (MMA).

### Usage

Duracon<sup>®</sup> 101 is used as a general prime coat for Duracon<sup>®</sup> floor coatings. It is normally used as supplied but may be thinned with Duracon<sup>®</sup> 407 to increase the penetration into certain types of cementitious substrates. For bituminous substrates we recommend the use of Duracon<sup>®</sup> 106 as primer. For ceramic and common metal substrates we recommend the use of Duracon<sup>®</sup> 107 as primer.

For information on above products please see the respective Data Sheets.

We strongly recommend with all Duracon<sup>®</sup> primers that curing and adhesion tests are conducted on the particular substrate prior to general use on site.

### Packaging

180 kg steel drums, 20 kg metal pails

### Shelf life

6 months when stored in a cool and dry place and in originally closed packaging. The optimal storage temperature is 15 - 20°C.

## TECHNICAL INFORMATION

### Technical characteristics (liquid state)

Viscosity, 25°C:	100-130 mPa*s	DIN 53018
Density, 25°C:	0.99 g/ml	ISO 2811
Pot life / processing time at 20°C:	approx. 15 min.	
Curing time at 20°C:	approx. 30 min.	
Flash point:	+ 11.5°C	ISO 1516

### Technical characteristics (cured state)

Tensile strength:	10.3 N/mm <sup>2</sup>	ISO 527
Elongation at maximum strength:	0.62 %	
Elongation at fracture:	0.62 %	
Modulus of elasticity:	1990 N/mm <sup>2</sup>	
Density, 20°C:	1.16 g/cm <sup>3</sup>	ISO 1183

Please note that an objective comparison with other data is only possible if norms and parameters are identical.

## USAGE GUIDELINES

### Substrate preparation

The substrate must be dry (maximum 4% residual humidity), firm, solid and free of dust, fat and oil. Laitance and loose particles must be thoroughly removed, e.g. by shot blasting. Fats or oils as well as humidity can be removed for example by flame blasting.

For further details, see our „General Preparation and application guidelines for Duracon<sup>®</sup> floor protection systems“.

### Mixing

Prior to use, Duracon<sup>®</sup> 101 must be carefully stirred to achieve a uniform distribution of the paraffin contained in the product. Duracon<sup>®</sup> 101 is thoroughly mixed together with the Duracon<sup>®</sup> CATALYST (50% dibenzoyl peroxyde), in accordance with the below guidelines.

It should be noted that the amount of catalyst powder to be added depends upon the temperature.

# DURACON® 101

Date: 10.08.2010  
Data Sheet: F0110GB01  
Page: 2 / 2

at 30°C add 1% by weight of resin  
at 20°C add 2% by weight of resin  
at 10°C add 4% by weight of resin  
at 0°C add 6% by weight of resin  
below 0°C add 6% by weight of resin and additionally add Duracon® 404, which is an accelerating agent.

Please contact our Technical Service Department for further details.

Note: Weight to Volumetric conversion of Catalyst.

1 cm<sup>3</sup> of Duracon® CATALYST weighs 0.64 g

1 g of Duracon® CATALYST = 1.57 cm<sup>3</sup>

## Application

After the catalyst has been stirred in, the primer is poured onto the substrate in stripes and distributed with a short-pile paint roller. A notched rubber squeegee can be used for fast distribution of large quantities. Apply at a rate of between 300 gr/m<sup>2</sup> to 500 gr/m<sup>2</sup> depending on density and porosity of the substrate. In any case, continue applying primer until saturation occurs to obtain a continuous resin film. On extremely porous substrates a second prime coat may be required. When a continuous resin film is obtained, broadcast fire-dried quartz sand (particle size 0.7 - 1.2 mm or 0.3 - 0.7 mm) into the still wet primer. Consumption approximately 0.3 kg/m<sup>2</sup>.

For further details see our „General Preparation and application guidelines for Duracon® floor protection systems“.

## HEALTH AND SAFETY PRECAUTIONS

Suitable protective clothing, gloves and safety goggles must be worn during mixing and application of Duracon® 101.

In case of contact with eyes rinse immediately for a long period of time and consult a physician. In case of contact with skin clean immediately with water and soap.

Duracon® 101 is highly flammable; keep away from heat and all sources of ignition and do not smoke. The stirrer as well as all the other electric appliances used on the application site must be explosion-proof versions.

For further information see our Material Safety Data Sheet.

## TECHNICAL SERVICE


Contact RPM/Belgium N.V. / Alteco Technik GmbH.

## GUARANTEE

RPM/Belgium N.V. and Alteco Technik GmbH warrant all goods to be free from defects and will replace materials proven to be defective but make no warranty as to appearance of colour.

The information and recommendations herein are believed by RPM/Belgium N.V. and Alteco Technik GmbH to be accurate and reliable.

## CE CERTIFICATION

	
07	
EN 13813	
Duracon® 101 in Duracon® BC Duracon® TR Systems	
Reaction to Fire:	C <sub>FI</sub> – s1 (Duracon® BC) C <sub>FI</sub> – s1 (Duracon® TR)
Wear resistance:	Class AR 0.5